



1 Cresset Road, Midrand Industrial Park, Midrand

Tel: (011) 310 1161 Fax: (011) 310 1156 Email: info@cretesol.co.za

Cretesol (Pty) Ltd Reg. No.2010/023146/07

HOW-TO-APPLY Cretesol Kiln Dried Silica Sand

1. POUR ON



Pour the jointing sand onto the dry surface and mix it with a spade to ensure the best mixing of grain size.

2. WORK IN



Work Cretesol's Kiln Dried Silica Sand in to the joints using a broom. To achieve comprehensive filling of the joint, always sweep diagonally to the joint and fill the jointing sand up to the top edge of the paving stone or the bevel.

3. COMPACTION



Use a vibratory plate as long as the surface is suitable for vibratory plates. If necessary, use a protective mat.

4. REFILL JOINTS



Refill the joints up to the top edge of the paving stone or the bevel. Sweep the surface carefully using a fine hair broom until no more sand is on the stone surface.

PLEASE NOTE: Cretesol Kiln Dried paving sand is suitable for 1-5mm joint widths. For bigger joints, we recommend our resin-based grouting solutions.